



# Soudaseal EPDM

Revision: 1/03/2016 Page 1 from 2

### **Technical data**

Basis	SMX Hybrid Polymer
Consistancy	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 10 min
Curing speed * (20°C / 65% R.H.)	2 mm/24h → 3 mm/24h
Hardness	50 ± 5 Shore A
Density	Ca. 1,62 g/ml
Elastic recovery (ISO 7389)	> 75 %
Maximum allowed distortion	± 20 %
Temperature resistance	-40 °C → 90 °C
Max. tension (DIN 53504)	> 2,00 N/mm²
Elasticity modulus 100% (DIN 53504)	0,75 N/mm²
Elongation at break (DIN 53504)	300 %
Consumption (*)	Ca. 15 linear meters at the recommended adhesive
	bead of about 5mm.
Application temperature	$5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$

<sup>(\*)</sup> these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

## **Product description**

Soudaseal EPDM is a high quality, neutral, elastic, 1-component Hybrid polymer based adhesive sealant for bonding and sealing of EPDM membranes in interior and exterior applications. Soudaseal EPDM is part of Soudal Window System.

# **Properties**

- Very good adhesion to EPDM membranes
- Good adhesion on most common building materials.
- Primerless adhesion even on damp surfaces due to unique adhesion promoters.
- Easy to tool, extrude (even at low temperatures) and finish in all weather conditions.
- Meets GEV EMICODE EC-1R Plus: very low emission
- Stays elastic after curing and very sustainable
- Solvent, halogen, acid and isocyanate free.
- UV resistant, waterproof and resistant to weathering

For in and outdoor use

### **Applications**

- For bonding of EPDM vapor barriers and waterproofing membranes in facade applications.
- For bonding and sealing of EPDM membranes to eachother as well to structural work, masonry, concrete, plaster, cement, aluminium, wood, etc.
- Particularly suitable for making airtight connections in window installations.

# **Packaging**

Colour: black

Packaging: 600 ml sausage

# Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





# Soudaseal EPDM

Revision: 1/03/2016 Page 2 from 2

### **Substrates**

Substrates: various porous and non-porous surfaces such as wood, concrete, stone and other materials commonly used in construction. As well as good adhesion (wet) surfaces: plaster, brick, (gas) concrete, wood, insulation, plasterboard, fiber cement, ... Not suitable for bitumen, PP, PE, PTFE and silicones. Nature: clean, free of dust and grease, can be moist.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. We recommend a preliminary adhesion test on every surface.

### **Application method**

Application method: With manual- or pneumatic caulking gun. Apply Soudaseal EPDM without interruptions in a bead of approx. 5 mm to the substrate. Place the EPDM membrane free of tension in the adhesive layer and press. A non-interrupted adhesive layer with a thickness of 1 to 2mm and a width of approx. 25mm guarantees the best curing.

Cleaning: Soudaseal EPDM can be removed before curing from tools and material with Soudal Adhesive Cleaner 90A, Swipex or white spirit. After curing can only be removed mechanically.

Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account.
Consult label and material safety data sheet for more information.

## Remarks

 Do not use in applications where continuous water immersion is possible.

#### **Environmental clauses**

Leed regulation:

Soudaseal EPDM conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOCcontent.

## Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com