

Thermafleece UltraWool

Technical Data Sheet



Thermal	
Thermal Conductivity	0.035 Wm ⁻¹ K ⁻¹
Density	31 kg/m ³
Specific Heat Capacity	1800 Jkg ⁻¹ K ⁻¹
Vapour Resistivity	9 MNsg ⁻¹ m ⁻¹

Material Protection	
Mould Resistance CUAP 2002-01-25	Pass
Moth/Beetle Proofing ISO 3998	Pass

Fire	
BS 5803-4, Flammability & Smoulder Resistance	Pass
EN11925-2, Reaction to Fire	Pass
Fire Classification	EuroClass E

Physical	
Recoverability and thickness, EN 823	Pass
Dimensional stability to EN 1604	Pass

Hygrothermal						
Porosity	23.8 %					
'Surface' water absorption coefficient (kg/m ² . h ^{0.5})	1.49 (7.7%)					
'Edge' water absorption coefficient (kg/m ² . h ^{0.5})	0.79 (6.0%)					
Water Vapour Resistance Factor, μ	(-) Dry: 1.99 (5.8%) (-) Wet: 0.89 (7.7%)					
Vapour sorption:						
Relative Humidity						
Sorption	0%w/w	30%w/w	50%w/w	75%w/w	95%w/w	
Moisture Content	0.00%	5.20%	7.91%	11.05%	16.74%	
Deviation		(4.7%)	(7.9%)	(6.3%)	(11.0%)	
Relative Humidity						
Desorption	95%w/w	75%w/w	50%w/w	30%w/w	0%w/w	
Moisture Content	16.74%	11.10%	9.42%	7.95%	0.00%	
Deviation	(11.0%)	(8.8%)	(5.2%)	(8.5%)		

Thermafleece UltraWool

Technical Data Sheet



Environmental	
GWP (A1-A3) total	0.11 kgCO ₂ e R1 Functional Unit
GWP (A1-C4)	1.44 kgCO ₂ e R1 Functional Unit
GWP (A1-D)	-0.50 kgCO ₂ e R1 Functional Unit
Recycled Content	20%
Recyclable	Yes
EPD registration no	S-P-04468
EPD valid to	31/10/26

Acoustic							
Sound absorption		NRC 1.10 @ 90mm					
Sound reduction		R _w 41dB -54dB @ 70mm					
Can be used to achieve airborne sound reduction of R _w		41dB					
Freq HZ		125	250	500	1000	2000	4000
UltraWool 50mm	Absorption Coefficient	0.2	0.55	0.85	0.9	1	1
UltraWool 90mm		0.5	1	1	1	1	1

Air Quality	
TVOC	9 µg/m ³ @ 3 days, n.d. @ 28 days
Carcinogenic compounds	n.d. @ 3days, n.d. @ 28days
Formaldehyde	<2 µg/m ³ @ 3 days, <2 µg/m ³ @ 28 days

Quality	
Manufactured to ISO 9001 & 14001	

Dimensions	
Thicknesses (+20mm/-0mm)	50,70,90 mm
Widths (+20mm/-0mm)	390 & 590 mm
Slab Length (+25mm/-25mm)	1200 mm, all sizes